

Product Data Sheet

No. **26075** - 04/11

DRY FILM LUBRICANT

AEROSOL

PRODUCT NUMBERS: 6075

I. GENERAL DESCRIPTION

Description: A non-staining product that forms a slippery layer of translucent particles on rubber, wood, metals, nylon, epoxies, polypropylene, acrylics, and phenolic resins. Dry Film Lubricant is a dispersion of white, waxy particles of PTFE.

Benefits: This film has unique dry lubricating qualities. Excellent for temperatures up to 500° F for extended periods. This product reduces clean-up labor time and will not interfere with post-finishing operations.

Application: This product is ideal for extreme dust conditions, such as encountered in mining and quarry operations. Use on conveyors, chutes, precision and electrical equipment.

Directions: Shake can well. Hold 8 to 10 inches from surface and apply uniformly. For best results, can should be at room temperature 70° F (21° C). Do not use on electrical equipment or machinery while in operation.

Limitations: Please refer to the Material Safety Data Sheet for specific information on material hazards, etc. For industrial use in manufacturing facilities.

Packaging:

Cans - (211 x 604)	11 oz. net wt.. (300 grams)	14.6 fl. oz. (432 ml)
Case - 12 cans/case	13 lbs. (5.9 kg)	0.55 CF (0.016 CM)



AerVOE Industries, Inc.
P.O. Box 485, Gardnerville, NV 89410



Wind'N'Go



SOLA DYNE



eZest

(775) 783-3100 Phone • (775) 782-5687 Fax • (800) 227-0196 Customer Service
www.aerVOE.com • mailbox@aerVOE.com

II. CHARACTERISTICS & PROPERTIES

Specifications:

NFS listed USDA H2

Appearance:

Non-foaming liquid

Color:

Light milky

Odor:

Ketonen

Dry Schedule:

N/A

Performance and Chemical Properties:

Weight per gallon	5.8 lbs
Specific gravity	0.70
Viscosity	N/A
Flammability: Label marking	Extremely Flammable
Flash point	<0° F (-18° C)
Operating temperature range	40° F to 110° F (5° to 43° C)
Active ingrediants by weight	2%
Volatile Organic Compound Level	72%
Dielectric strength	TBD
Lubricity (FALEX FLC Test)	200 ft. lbs.
Penetrating ability	Excellent
Corrosion protection	Good
Food contact rating	H2

Base Materials:

..... PTFE, Acetone

Propellent:

..... Hydrocarbon

III. SHIPPING, STORAGE AND HEALTH

IMDG number	UN 1950
D.O.T. container spec	2P
D.O.T. shipping description	Consumer commodity
Warehouse storage level number	NEPA 30B Level 2
Hazardous Class (CFR-49)	ORM-D
Storage temperature	32° to 120°F (0° to 49°C)
Shelf life	1 to 5 years
HMS ratings	
Health	2
Fire	4
Reactivity	0

IV. MISCELLANEOUS

Contains no Ozone Depleting Substances (O.D.S.)

V. WARRANTY

The statements made herein, on labels, product bulletins or by any of our employees or agents concerning this material are given for information only. Any liability whatsoever of Aervoe Industries, Inc. to the user of the product, is limited to replacement of the product or purchase price refunded.